

Super High Strength™

Extreme Tear and Tensile Strength

Technical Datasheet



A superior quality medium hardness jewelry molding rubber with extreme tear and tensile strength for every application including spirals, cores, cut-outs & plugs as well as for general purpose use. Can be used with Econosil® on the outside for additional stiffness or on the inside for additional dimension stability. Can also be used with SuperStretch for cores and spirals.

Super High Strength is a tan color and is lined with special release paper on both sides. Complete instructions are enclosed in each box. For a more complete description and detailed instructions, please refer to our free technical bulletin.

Super High Strength Jewelry Molding Rubbers is available in: Traditional strips: 18" x 2 7/8" x approximately 3/8" / 45.7 cm x 7.3 cm x approximately 6 mm. Packaged in attractive, consumer-oriented boxes weighing 5 lbs. / 2.27 kg. It is packed 10 boxes to a carton for a total net weight of 50 lbs. / 22.7 kg.

Name	Super High Strength
Shore A Hardness	38-40
Vulcanizes at	165 - 176°C
Rubber Shrinkage	Medium 2.3%
Break Elongation	667%
Break Tensile Strength	8.3 n/mm ²
Break Tear Strength	21.2 n/mm ²
Uses	High Strength, General Purpose

*Shrinkage rates given are for the rubber mold itself. Final casting shrinkage rates depend on moldmakers and caster's skill, knowledge, precision and attention to detail.



Silicone Molding Rubber



Castaldo Silicone Molding Rubber is soft and pliable, with a consistency like putty or molding clay.


Mold frame packing with Castaldo Silicone Molding Rubber is fast, easy and requires no tools.



Placing and embedding the model exactly as you want it is simple.



Curing Castaldo Silicone Jewelry Molding Rubber Molds involves no mixing, limited working times or de-bubbling. Simply put it in your vulcanizer at 330°-150°F (165°-177°C) for 15 minutes per 1/4 inch (6mm).



Castaldo Silicone Jewelry Molding Rubber Molds are easy to cut, reducing hand fatigue and increasing control. Users say they "Cut like butter".



Parting lines are easily controlled and corrected by hand when used with the powder separation technique.



Finished molds can be simple or complex with cores, straight plugs or even spiral plugs. Castaldo Silicone Jewelry Rubber Molds are strong and tear resistant and can last for years and years.

BURNING IN SPRUES: CASTALDO® silicone jewelry molding rubbers can be burned in the usual manner to add sprues or correct details but higher temperatures are needed. Use adequate ventilation!

CAUTION: Vapors given off during vulcanization may produce temporary eye, nose and throat irritation among certain susceptible individuals. Use with adequate ventilation.

STORAGE: As with any unvulcanized rubber compound, store away from any source of heat and light. Unvulcanized shelf life is at least one year if properly stored except for low-temperature cure compounds. The storagelife of those compounds can be severely shortened by unintentional exposure to heat in shipping and storage.